
APPLYING ARC 858 WITH THE SULZER MANUAL GUN

THE SULZER MANUAL GUN IS CAPABLE OF DISPENSING ARC PRODUCTS WITH 2:1 AND 4:1 MIX RATIOS



IT IS DESIGNED TO EXTRUDE PRODUCT THROUGH A STATIC MIXER, AND IS <u>INCAPABLE</u> OF SPRAYING ARC COATINGS






EACH MANUAL GUN COMES WITH AN ARRAY OF PLUNGER DISCS DESIGNED TO FIT SULZER CARTRIDGES.

CURRENT ARC PRODUCTS UTILIZE EITHER THE 2:1 OR

4:1 (ARC 858)







BAND HEATERS AND PAIL HEATING BLANKETS ARE
OTHER ALTERNATIVES FOR HEATING THE
CARTRIDGES STORED IN 5 GALLON PAILS.


TEMPERATURE RECOMMENDATION 115 F – 125 F (46C - 52C)








FAILURE TO PREHEAT THE COATING WILL CREATE BACKPRESSURE AS THE HANDLE IS DEPRESSED, RESULTING IN THE COMPONENTS EXTRUDING BETWEEN THE CARTRIDGE END CAP AND CARTRIDGE WALL.



























UPON INITIAL USE, THE ARC 858 MAY
APPEAR BLACK IN COLOR DUE TO
INCOMPLETE MIXING IN THE STATIC
MIXER. THIS IS NORMAL. WHEN THE ARC
858 IS GREY, IT IS "ON RATIO" AND
READY FOR USE.

STATIC MIXERS CAN NOT BE REUSED





- SULZER MANUAL GUN PART NUMBER 084773
- STATIC MIXERS ARC 858 (940 ML) 4:1 PART NUMBER 084242 QUANTITY OF 10 MIXERS PER PACKAGE
- STATIC MIXERS ARC S2, ARC SD4i, ARC S1PW, ARC S4+ (1125 ML) 2:1
 PART NUMBER 082882 QUANTITY OF 10 MIXERS PER PACKAGE